



3202 34th Street, Valley, AL 36854

Telephone: 334-768-1262 or 1-800-554-7424 Fax: 334-768-1255

Textest Report: 1198730
Date: 04/21/08
Page: 1 of 5
Purchase Order: KC0803

CLIENT:



Reflective Apparel Factory
1649 Sands Place SE Suite J
Marietta, Georgia 30067

Material Description: 100% Polyester Knitted Mesh, 128 gsm $\pm 5\%$	
Fabric ☒ Non-Fabric ☐	(check one)
Lot #:	
Manufacturer:	
Color: HiVis Yellow	

COMMENT:

We certify that the sample identified above was tested in accordance with the specification and complies with the requirements for background materials of ANSI/ISEA 107-2004.

Material: 100% polyester Micro Mesh with wicking finish.
for items: VEA100, VEA103

TEXTTEST

Signed by

Material Description:	100% Polyester Knitted Mesh 128 gsm $\pm 5\%$	Test Lab:	 Report #1198730
Fabric ☒ X ☐	Non-Fabric ☐ (check one)	Address:	3202 34th Street Valley, AL 36854
Lot #:		Contact Person:	Alan Lightholder
Manufacturer:		Date Tested:	4/21/2008
Color:	HiVis Yellow		

REQUIRED TESTS				
Test/Method	Section	ANSI/ISEA 107 Requirement	Test Result	Pass/ Fail/ NA
Determination of Color ASTM E1164-02 (Single layer)	7.1.1 9.2	Test specimen must fulfill the colorimetric requirements of Table 2 for background material	As submitted: x = 0.373 y = 0.535 %Y = 82.2 After 40x Xenon x = 0.368 y = 0.496 %Y = 76.9	Pass Pass Pass Pass Pass Pass
Determination of Color ASTM E1164-94 (Two layers of the same material)	7.1.1 9.2	Test specimen must fulfill the colorimetric requirements of Table 2 for background material	As submitted: x = y = %Y = After 40x Xenon x = y = %Y =	NA NA NA NA NA NA
Colorfastness Croaking AATCC 8-2001	7.2.1	Wet 3.0 Dry 3.0	4.0 4.0	Pass Pass
Colorfastness Perspiration AATCC 15-2002	7.2.2	Color Change 4.0 Staining 3.0	5.0 Acetate: 4.0 Cotton: 4.0 Nylon: 4.0 Polyester: 4.5 Acrylic: 4.5 Wool: 4.5	Pass Pass Pass Pass Pass Pass Pass
Dimensional change Domestic AATCC 135-2000 (3) IIIA(iii) @105°F	7.3.1	Woven L +/- 4% W +/- 2%	1st Cycle Length = Width = 5th Cycle Length = Width =	NA NA NA NA
		Knit L +/- 7% W +/- 5%	1st Cycle Length = Width = 5th Cycle Length = - 3.7 Width = - 2.3	NA NA Pass Pass

Material Description:	100% Polyester Knitted Mesh 128 gsm $\pm$ 5%	Test Lab:	 Report #1198730
Fabric <u> X </u>	Non-Fabric <u> </u> (check one)	Address:	3202 34th Street Valley, AL 36854
Lot #:		Contact Person:	Alan Lightholder
Manufacturer:		Date Tested:	4/21/2008
Color:	HiVis Yellow		

REQUIRED TESTS (cont)				
Test/Method	Section	ANSI/ISEA 107 Requirement	Test Result	Pass/ Fail/ NA
Bursting Strength (Knitted) ASTM D 3787-01	7.4.1	267 N (60 lb) (27.2 kg)	117 lb.	Pass
Tear Resistance (Woven) ASTM D 1424-96	7.4.2	13 N (3 lb) (1.3 kg) Average force machine Average force cross-machine		NA NA
Breathability ASTM E96-00 Procedure B ASTM E96-00 Procedure BW	7.6	600g/m ² /24 hr microporous 3600g/m ² /24 hr hydrophilic		NA NA

TESTED AS CARE LABEL DICTATES				
Test/Method	Section	ANSI/ISEA 107 Requirement	Test Result	Pass/ Fail/ NA
Colorfastness Domestic Laundry AATCC 61-2001-2A 120° F	7.2.3 Table 4	Color change 4.5 Staining 3.0	Acetate: Cotton: Nylon: Polyester: Acrylic: Wool:	NA NA NA NA NA NA
Colorfastness Commercial Laundry AATCC 61-2001-3A 160° F	7.2.3 Table 4	Color change 4.5 Staining 3.0	Acetate: Cotton: Nylon: Polyester: Acrylic: Wool:	NA NA NA NA NA NA
Colorfastness Domestic Laundry AATCC 61-2001-2A 105° F	7.2.3 Table 4	Color change 4.5 Staining 3.0	4.5 Acetate: 3.5 Cotton: 4.5 Nylon: 3.5 Polyester: 4.5 Acrylic: 4.5 Wool: 4.0	Pass Pass Pass Pass Pass Pass Pass

Material Description:	100% Polyester Knitted Mesh 128 gsm $\pm 5\%$	Test Lab:	 Report #1198730
Fabric ☒ X ☐	Non-Fabric ☐ (check one)	Address:	3202 34th Street Valley, AL 36854
Lot #:		Contact Person:	Alan Lightholder
Manufacturer:		Date Tested:	4/21/2008
Color:	HiVis Yellow		

TESTED AS CARE LABEL DICTATES (cont)

Test/Method	Section	ANSI/ISEA 107 Requirement	Test Result	Pass/ Fail/ NA
Colorfastness Water AATCC 107-2002	7.2.3 Table 4	Color change 3.0 Staining 3.0	5.0 Acetate: 4.0 Cotton: 4.0 Nylon: 4.0 Polyester: 4.5 Acrylic: 4.5 Wool: 4.5	Pass Pass Pass Pass Pass Pass Pass
Colorfastness Hypochlorite Bleaching AATCC 61-2001-4A	7.2.3 Table 4	Fading 4.0		NA
Colorfastness Hypochlorite Bleaching AATCC 61-2001-5A	7.2.3 Table 4	Fading 4.0	4.5	Pass
Colorfastness Hot-pressing AATCC 133-1999	7.2.3 Table 4	Color change 4.5 Staining 3.0	5.0 5.0	Pass Pass
Colorfastness Dry cleaning AATCC 132-2001	7.2.3 Table 4	Color change 4.0		NA
Dimensional change Commercial AATCC 96-1999 IIIc-A and/or E@ 145° F	7.3.1	Woven L +/- 4% W +/- 2%	1st Cycle Length = Width =	NA NA
			5th Cycle Length = Width =	NA NA
		Knit L +/- 7% W +/- 5%	1st Cycle Length = Width =	NA NA
			5th Cycle Length = Width =	NA NA
Water Resistance AATCC 35-2000	7.5	1 gram of water penetration Level 1		NA
Water Resistance AATCC 127-1998	7.5	200 cm Min. new 200 cm Min. after 5 washings		NA NA
Water Repellence AATCC 22-2001	7.5.1	90 new 70 after 5 washings		NA NA

Material Description:	100% Polyester Knitted Mesh 128 gsm $\pm 5\%$	Test Lab:	TEXT [®] Report #1198730
Fabric ☒ X ☐	Non-Fabric ☐ (check one)	Address:	3202 34th Street Valley, AL 36854
Lot #:		Contact Person:	Alan Lightholder
Manufacturer:		Date Tested:	4/21/2008
Color:	HiVis Yellow		

CIE 1931 (x,y) Chromaticity Diagram

