


TexTesT Report: 1224638
 Date: 03/30/10
 Page: 1 of 1

CLIENT: REFLECTIVE APPAREL FACTORY
 1739 Sands Place Suite D
 Marietta, GA 30067

 ATTN: Rich Boven

SAMPLE IDENTIFICATION: VEA Birdseye Knit Fabric 4.1 osy
 Fluorescent Yellow

DETERMINATION OF COLOR ANSI-107-2010 (1 layer of background material) After 76 washes *	Pass / Fail	ANSI-107-2010 Requirements Table 2 Color, background material Yellow-Green		
		chromaticity coordinates x	y	luminance factor
Luminance (Y) %	107.2 Pass	0.387	0.610	70.0%
x rating	0.387 Pass	0.356	0.494	
y rating	0.534 Pass	0.398	0.452	
* AATCC 135 (3, III, Aiii)		0.460	0.540	
Mashine wash 105°F				
Permanent Press Cycle				
Tumble Dry Permanent Press				



TEXTTEST

Alan Lightholdus

signed by